



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: A61K 38/24, 38/04, 9/14, 9/52	A1	(11) International Publication Number: WO 00/40259 (43) International Publication Date: 13 July 2000 (13.07.00)
(21) International Application Number: PCT/KR99/00071 (22) International Filing Date: 11 February 1999 (11.02.99) (30) Priority Data: 1998/62142 30 December 1998 (30.12.98) KR (71) Applicant (for all designated States except US): DONG KOOK PHARMACEUTICAL CO., LTD. [KR/KR]; 997-8, Taechi-dong, Kangnam-ku, Seoul (KR). (72) Inventors; and (75) Inventors/Applicants (for US only): BAEK, Myoung, Ki [KR/KR]; 302, 294-3, Sukchon-dong, Songpa-ku, Seoul (KR). PARK, Jin, Kyu [KR/KR]; 4-206, Hanyang Apt., 54, Myoungil-dong, Kangdong-ku, Seoul (KR). PARK, Mork, Soon [KR/KR]; 105-902, Youngjinroyal Apt., Joongli-dong, Taeduck-ku, Taejon (KR). PARK, Tae, Kwan [KR/KR]; 211-1501, Expo Apt., Chunmin-dong, Yusung-ku, Taejon (KR). CHOI, Seung, Ho [KR/KR]; 301, Sangrok Villa, 524-3, Deungchon 2-dong, Kangseo-ku, Seoul (KR). (74) Agents: HWANG, E-Nam et al.; Yegun Building, 3rd floor, 823-42, Yoksam-dong, Kangnam-ku, Seoul 135-080 (KR).		(81) Designated States: BR, CA, CN, IN, JP, MX, TR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PROLONGED RELEASE MICROSPHERE ENCAPSULATING LUTEINIZING HORMONE-RELEASING HORMONE ANALOGUES AND METHOD FOR PREPARING THE SAME (57) Abstract <p>There is disclosed a prolonged release microsphere which can constantly release medicinal drugs, such as luteinizing hormone-releasing hormone analogues and encapsulate them at high content rates. It is prepared by dissolving a copolymer of lactide and glycolide in methylene chloride, dissolving a luteinizing hormone-releasing hormone analogue and a release-controlling material in a subsidiary solvent, combining the above two solutions with each other to produce an emulsion phase, dispersing the emulsion phase in a solution of polyvinyl alcohol in distilled water to give a single emulsion system, removing the combined solvent of the emulsion phase to generate a polymeric microsphere; freeze-drying the polymeric microsphere. The microsphere prepared has a much finer inner structure, by virtue of which the microsphere is secured in a constant release rate. The single emulsion system which simplifies the preparation, allows for the maintenance of a drug content of 10 % or more. The charged groups of the release-controlling materials associated with the polymers minimize the excess release of the oppositely charged drugs at an initial stage, playing an important role in keeping the release rate constant.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

-1-

PROLONGED RELEASE MICROSPHERE ENCAPSULATING LUTEINIZING HORMONE-RELEASING HORMONE ANALOGUES AND METHOD FOR PREPARING THE SAME

Technical Field

5 The present invention relates to a microsphere encapsulating luteinizing hormone-releasing hormone (hereinafter referred to as "LHRH") analogues, which is able to constantly release them for a long period of time. Also, the present invention is concerned with a method for preparing such a prolonged release microsphere.

10 Background Art

Physiologically, when testosterone or estrogen is in a low concentration level in blood or when hypothalamic-releasing hormone is stimulated, gonadotropin-releasing hormone (hereinafter referred to as "GnRH") is secreted from the hypothalamus. The GnRH is then
15 transferred through the hypothalamic-pituitary portal system to the pituitary gland at which the GnRH stimulates the synthesis and secretion of luteinizing hormone (hereinafter referred to as "LH") and follicle stimulating hormone. As a result, testosterone or estrogen is secreted.

LHRH analogues act on the pituitary gland to inhibit the secretion
20 of LH, thus resulting in the antagonizing of the liberation of testosterone and estrogen into the bloodstream. By taking advantage of this antagonistic action, the diseases caused by testosterone and estrogen, such as prostatic cancer, breast cancer, endometriosis and the like, have recently been therapeutically treated.

25 Like general peptide drugs, LHRH is, however, very instable within the gastro-intestinal tract and shows a low uptake efficiency therein. Therefore, the administration of LHRH has been usually performed via injection. The administration via injection also has a significant disadvantage of being very poor in bioavailability so that LHRH is
30 required to be injected daily. Such injection administration also requires a long cure period, which causes a problem in a patient's adaptation to the drug, therapeutic efficiency, and treatment.

Extensive research has been made on the use of poly(lactide-co-

-2-

glycolide) (PLGA), which is an intravital degradable polymer, in controlled releasable dosage forms which contain proteins or peptides. The released form and structural stability of proteins with high molecular weights are the most difficult barriers in commercializing them into medicinal drugs. In result, research efforts have been and continue to be directed to the development of various additives and new preparation processes by which the proteins can be commercialized while maintaining their activity.

For peptide drugs, commercialization is relatively easy because peptides are smaller in size and stabler than proteins. As commercialized examples, there are sustained-release DOS preparations containing LHRH analogues, which are peptides with a molecular weight of 1.2 kDa.

The microspheres made of PLGA are decomposed into lactic acid and glycolic acid by hydrolysis in the body and metabolized. In other words, PLGA is not harmful to the human body nor shows side effects from the decomposed products. What is better, the microspheres made of PLGA can release their contents, e.g. therapeutically effective ingredients, at a constant rate for a desired period of time.

In this regard, U.S. Pat. No. 4,711,782 introduces a technique for producing microporous microcapsules from similar polymers by W/O/W (water in oil in water) double emulsification. This technique is usually used to capsule water-soluble drugs. In this technique, when a water-soluble drug is dissolved in water, gelatin is used together to retain the drug, and this aqueous layer is dispersed in an organic layer containing the polymer with the aid of a homogenizer, so as to give a primary emulsion. Again, this primary emulsion is dispersed in water containing polyvinyl alcohol as a surfactant, to give a secondary emulsion. The organic solvent is diffused into the aqueous layer and evaporated, so that the polymer is solidified to form the microcapsules. They are then freeze-dried.

As mentioned, water is used to dissolve water-soluble peptides and the microcapsules obtained are of porous structure. Thus, these microcapsules have a problem of being so high in the initial release rate of peptide drugs and low in drug content.

Disclosure of the Invention

The intensive and thorough research on a prolonged release microsphere, repeated by the inventors aiming to release peptide drugs continuously for an extended period of time, resulted in the finding that, when an appropriate combination of two poly(lactide-co-glycolide) copolymers, which have an equimolar ratio between their lactide moiety and glycolide moiety and have a carboxyl group and a dodecyl group at their ends, is used as a carrier for drug, the microsphere is enhanced in biodegradation rate as well as in drug content. The negative charge of the carboxyl group attached to the end of the biodegradable polymer form an ion bond with the positive charges that the peptide drugs possess, increasing the drug content in the microsphere and preventing the drugs from being released excessively at an initial time due to diffusion. The dodecyl group plays an important role in controlling the degradation rate of the microsphere. Consequently, the microspheres in the body release LHRH analogues continuously to maintain the concentration of testosterone and estrogen in blood for an extended period of time, so as to improve the therapeutic efficiency of and the patient's adaptation to the drugs.

Therefore, it is an object of the present invention to provide a prolonged release microsphere which can control the release of drugs for a sustained period of time.

It is another object of the present invention to provide a prolonged release microsphere which is high in the content of therapeutically effective ingredients.

It is a further object of the present invention to provide a method for preparing such a prolonged release microsphere with ease and a good efficiency.

In accordance with an aspect of the present invention, there is provided a prolonged released microsphere, which is composed of a poly(lactide-co-glycolide) copolymer and encapsulate a luteinizing hormone-releasing hormone analogue.

In accordance with another aspect of the present invention, there is provided a method for preparing a prolonged release microsphere, comprising the steps of: dissolving a copolymer of lactide and glycolide in methylene chloride; dissolving a luteinizing hormone-releasing

-4-

hormone analogue and a release-controlling material in a subsidiary solvent; combining the above two solutions with each other to produce an emulsion phase; dispersing the emulsion phase in a solution of polyvinyl alcohol in distilled water to give a single emulsion system; removing the combined solvent of the emulsion phase to generate a polymeric microsphere; and freeze-drying the polymeric microsphere.

Best Modes for Carrying Out the Invention

In the present invention, a microsphere which retains therapeutically effective drugs and continuously releases them for a sustained period of time, is prepared from a mixture of biodegradable polymers. As therapeutically effective drugs, LHRH analogues are of particular interest. Therefore, if the microspheres retaining LHRH analogues are administered, they release the drugs for a long period of time, whereby testosterone or estrogen can be maintained at a low level in the blood and an improvement in therapeutic effect and patient's adaptation to the drugs can be brought about.

The prolonged release microsphere which encapsulates LHRH analogues has an aporous, fine and uniform inner structure, so that its drug content rate is enhanced.

The microsphere can be prepared in a single emulsion process. In detail, LHRH analogues, including goserelin acetate, nafarelin acetate, buserelin acetate and leuporelin acetate, are dissolved in a subsidiary solvent and added to an organic solvent containing a polymer to give an oil phase which is then dispersed in an aqueous phase.

A preferred example of the organic solvent useful in the invention is methylene chloride. The aqueous phase is obtainable by dissolving polyvinyl alcohol.

The subsidiary solvent which dissolves LHRH should be miscible with the organic solvent (methylene chloride) and water, both. Examples of the subsidiary solvent include N-methyl-2-pyrrolidone (NMP), dimethyl sulfoxide (DMSO), dimethyl formamide (DMF), acetone, ethanol, ethyl acetate, and methyl ethyl ketone (MEK) with the most preference to NMP. This subsidiary solvent plays an important role in providing the microsphere with an aporous fine structure.

In the present invention, the release of LHRH analogues is

-5-

controlled in a double manner by the actions of the functional groups, i.e. carboxyl group and dodecyl group, attached to the ends of the two polymers which compose the microsphere. The carboxyl group forms a hydrophobic ion pair with LHRH analogues, so the release rate thereof is retarded. The dodecyl group inhibits the enzymatic action to degrade the microsphere, so the integrity of the biodegradable microsphere is sustained. Therefore, the drug contained in the microsphere is not released in a sudden burst.

The compound suitable to retard the release rate of LHRH analogues must form the hydrophobic ion pair with LHRH analogues as well as can be dissolved in the organic solvent. Preferable examples to meet these standards include sodium oleate, deoxycholic acid, cholic acid, fatty acids and phosphatidic acids.

The biodegradable microsphere of the present invention is aporous with an ultrafine inner structure, as shown in Figs. 1 and 2. The data obtained from an *in vitro* release test demonstrate that LHRH is released at relatively constant rates from the microspheres of the invention, as shown in Fig. 3. The microspheres were measured for their weight loss in order to obtain the information about their biodegradation rates, which finally told that the microspheres are completely decomposed on around the 45th day after testing, as shown in Fig. 4. The data obtained from an *in vivo* release test, shown in Fig. 5, are well correlated with those of Fig. 4.

A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present invention.

EXAMPLE I : Preparation of Biodegradable Microsphere Containing Leuporelin acetate

A microsphere was made from biodegradable PLGA in an O/W (oil in water) mono-emulsification method.

In 3 ml of methylene chloride was dissolved 350 mg of each of a PLGA which has a dodecyl group at its end and a molecular weight of 12,000 with 50:50 lactide moiety:glycolide moiety, such as that sold by Boehringer Ingelheim under the brand name of RH502, and a PLGA which has a carboxyl group at its end and a molecular weight of 8,600

-6-

with 50:50 lactide moiety:glycolide moiety, such as that sold by Boehringer Ingelheim under the brand name of RH502H. This methylene chloride solution was sufficiently mixed with a solution of 100 mg of leuporelin acetate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.5 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a stirrer at 700 rpm for 30 min. While the emulsion was stirred for 3 hours under an atmosphere, N-methyl-2-pyrrolidone was extracted with water and methylene chloride was evaporated out, so as to give solidified microspheres. After being collected by centrifugation at 8,000 rpm for 30 min, the microspheres were centrifuged again twice with water to remove remaining solvent and drugs and then, freeze-dried.

EXAMPLE II : Preparation of Biodegradable Microsphere Containing Goserelin acetate

In 3 ml of methylene chloride were dissolved 100 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 25 mg of leuporelin acetate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 200 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a stirrer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

EXAMPLE III: Preparation of Biodegradable Microsphere Containing Nafarelin acetate

In 5 ml of methylene chloride were dissolved 200 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 50 mg of nafarelin acetate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a stirrer at 500 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

-7-

EXAMPLE IV: Preparation of Biodegradable Microsphere Containing Leuporelin Acetate using Homogenizer

In 5 ml of methylene chloride were dissolved 200 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 50 mg of leuporelin acetate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.5 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

EXAMPLE V: Preparation of Biodegradable Microsphere Containing Leuporelin acetate with Sodium Oleate

In 1 ml of methylene chloride were dissolved 200 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 50 mg of leuporelin acetate and 3.105 mg of sodium oleate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

EXAMPLE VI: Preparation of Biodegradable Microsphere Containing Sodium Oleate/Leuporelin Complex

17.5 mg of sodium oleate and 50 mg of leuporelin acetate were reacted in distilled water to yield precipitates which were, then, collected and freeze-dried. They were dissolved in a mixed solution of 0.66 ml of N-methyl-2-pyrrolidone and 1.33 ml of methylene chloride which contained 200 mg of each of RG502H and RG502. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the

-8-

remaining procedure of Example I.

TABLE I
Drug Content and Average Particle Size of the Microsphere

Examples	% Drug Content	Avg. Particle Size (μm)
I	10.76	138.5
II	9.98	106.8
III	10.21	122.1
IV	10.71	11.2
V	10.32	10.6
VI	11.21	10.4

TEST EXAMPLE I: *in vitro* Drug Release of Microspheres

The biodegradable microspheres prepared in Examples were tested for *in vitro* release as follows. 5 mg of the freeze-dried microsphere were dispersed in a vial containing a solution of 0.05% Tween 80 in 10 ml of a 0.333 M phosphate buffer and stored at 37 °C for 28 days. A test sample was taken every third day from the first day to the thirtieth day. The ten samples thus taken were centrifuged. After the removal of the supernatant, the microspheres were quantified for the drugs through an HPLC with a mobile phase of 3:1 ammonium acetate:methanol at a flow rate of 1.0 ml/min at 280 nm. The results were shown in Fig. 3.

TEST EXAMPLE II: Degradation of Microspheres

Under the same condition as that of Test Example I, a test sample was taken every fourth day. The samples were centrifuged, followed by the removal of the supernatant. The microspheres thus obtained were dried and accurately measured for their weights. From the measurements, the degradation rates of the microspheres were calculated, and shown in Fig. 4.

TEST EXAMPLE III: *in vivo* Drug Release of Microspheres

The biodegradable microspheres prepared in Examples were tested for *in vitro* release as follows. The microspheres were introduced into the femoral regions of rats via intramuscular injection and the remaining microspheres were taken from the femoral regions by incising the regions every fifth day. The microspheres taken were homogenized in 10 ml of a solution of 0.02 wt% Tween 80 (polyoxyethylene 20 oleate, Junsei Chemical Co.) in a 0.333 M phosphate buffer (pH 7.0). After further addition of 10 ml of the buffer and 10 ml of methylene chloride, the drugs were extracted in an aqueous layer. These extracts were quantified by HPLC under the same condition as that of the *in vitro* release test and the results are shown in Fig. 5.

Brief Description of the Drawings

Fig. 1 is an SEM photograph showing the microsphere of the present invention;

Fig. 2 is an SEM photograph showing a cross section of the microsphere of the present invention.

Fig. 3 is a plot showing the *in vitro* release rates of the microspheres against time.

Fig. 4 is a plot showing the weight loss rates of the microspheres against time.

Fig. 5 is a plot showing the *in vivo* release rates of the microspheres against time.

Industrial Applicability

As described hereinbefore, the microspheres prepared according to the present invention have much finer inner structures than do conventional microspheres, by virtue of which the microspheres are secure in a constant release rate. The single emulsion system of the present invention simplifies the preparation process of the microsphere, enabling it to maintain a drug content of 10% or more. In addition, the charged groups of the release-controlling materials associated with the polymers minimize the excess release of the oppositely charged drugs at

-10-

an initial stage, playing an important role in keeping the release rate constant.

5 The present invention has been described in an illustrative manner, and it is to be understood the terminology used is intended to be in the nature of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. Therefore, it is to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

CLAIMS

1. A prolonged released microsphere, which is composed of a poly(lactide-co-glycolide) copolymer and encapsulate a luteinizing hormone-releasing hormone analogue.
- 5 2. A prolonged released microsphere as set forth in claim 1, wherein the luteinizing hormone-releasing hormone analogue is selected from the groups consisting of goserelin acetate, nafarelin acetate, buserelin acetate and leuporelin acetate.
- 10 3. A prolonged released microsphere as set forth in claim 1, wherein the copolymer consists of a polylactide and a polyglycolide either of which have a dodecyl group and a carboxyl group at their ends.
- 15 4. A method for preparing a prolonged release microsphere, comprising the steps of:
 dissolving a copolymer of lactide and glycolide in methylene chloride;
 dissolving a luteinizing hormone-releasing hormone analogue and a release-controlling material in a subsidiary solvent;
 combining the above two solutions with each other to produce an emulsion phase;
20 dispersing the emulsion phase in a solution of polyvinyl alcohol in distilled water to give a single emulsion system;
 removing the combined solvent of the emulsion phase to generate a polymeric microsphere;
 freeze-drying the polymeric microsphere.
- 25 5. A method as set forth in claim 4, wherein the single emulsion system comprises 75.0-99.0 wt% of an aqueous phase and 0.3-0.5 wt% of polyvinyl alcohol and the emulsion phase comprises 0.50-10.0 wt% of methylene chloride and 0.2-10.0 wt% of the subsidiary solvent.
- 30 6. A method as set forth in claim 4 or 5, wherein the subsidiary solvent is N-methyl-2-pyrrolidone.


-12-

7. A method as set forth in claim 5, wherein the release-controlling material is capable of hydrophobic ion pairing with the luteinizing hormone-releasing hormone analogue and being dissolved in an organic solvent.

5 8. A method as set forth in claim 5 or 7, wherein the release-controlling material is sodium oleate and is used at an amount of 75-100 mol% based on the moles of the luteinizing hormone-releasing hormone analogue.

1/5


FIG. 1



BEST AVAILABLE COPY

2/5

FIG. 2




BEST AVAILABLE COPY

SUBSTITUTE SHEET (RULE 26)


3/5

FIG.3




4/5

FIG. 4



5/5

FIG.5



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR 99/00071

A. CLASSIFICATION OF SUBJECT MATTER

IPC⁷: A 61 K 38/24, 38/04, 9/14, 9/52

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC⁷: A 61 K 38/24, 38/04, 9/14, 9/52

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, CAS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 505 966 A1 (HOECHST AKTIENGESSELLSCHAFT), 30 September 1992 (30.09.92), page 2, lines 1-3,38-40,48-51.	1,2
X	US 4 835 139 A (TICE et al.), 30 May 1989 (30.05.89), column 1, lines 50-63; column 3, line 65 - column 4, line 15; example 1; claim 1.	1
A	US 5 540 937 A (BILLOT et al.), 30 July 1996 (30.07.96), column 5, line 62 - column 6, line 32; example 3.	1,2,4
A	US 5 192 741 A (ORSOLINI et al.), 09 March 1995 (09.03.93), example 1; claim 1.	1,2,4
A	US 4 675 189 A (KENT et al.), 23 June 1987 (23.06.87), example 1; claim 1.	1,2,4
A	GB 2 165 517 A (DEBIOPHARM SA), 16 April 1986 (16.04.86), example 1.	1,2,4

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

„A“ document defining the general state of the art which is not considered to be of particular relevance

„E“ earlier application or patent but published on or after the international filing date

„I“ document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

„O“ document referring to an oral disclosure, use, exhibition or other means

„P“ document published prior to the international filing date but later than the priority date claimed

„T“ later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

„X“ document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

„Y“ document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

„&“ document member of the same patent family

Date of the actual completion of the international search

27 September 1999 (27.09.99)

Date of mailing of the international search report

07 October 1999 (07.10.99)

Name and mailing address of the ISA/AT
Austrian Patent Office
Kohlmarkt 8-10; A-1014 Vienna
Facsimile No. 1/53424/200

Authorized officer

Mosser

Telephone No. 1/53424/437

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR 99/00071

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication	
EP A1	505966	30-09-1992	AT E	124254	15-07-1995
			AU A1	13109792	01-10-1992
			AU B2	653210	22-09-1994
			CA AA	2063883	26-09-1992
			CS AS	9200887	14-10-1992
			CY A	2032	20-02-1998
			CZ B6	284756	17-02-1999
			DE CO	59202649	03-08-1995
			DK T3	505966	30-10-1995
			EP B1	505966	28-06-1995
			ES T3	2076592	01-11-1995
			FI A0	921248	23-03-1992
			FI A	921248	26-09-1992
			FI B	99084	30-06-1997
			FI C	99084	10-10-1997
			HR A1	940838	30-06-1997
			IE B	67555	17-04-1996
			IL A0	101346	15-11-1992
			JP A2	5070363	23-03-1993
			NO A0	921147	24-03-1992
			NO A	921147	28-09-1992
			NO B1	302856	04-05-1998
			NZ A	242073	26-08-1993
			ZA A	9202130	25-11-1992
US A	4835139	30-05-1989	CH A	661206	15-07-1987
US A	5540937	30-07-1996	AU A1	42022793	10-02-1994
			AU B2	675788	20-02-1997
			CA AA	2100925	28-01-1994
			EP A1	585151	02-03-1994
			FR A1	2693905	28-01-1994
			FR B1	2693905	02-09-1994
			JP A2	6087758	29-03-1994
US A	5192741	09-03-1993	NZ A	248207	27-02-1996
			AT A	2234/88	15-06-1993
			AT B	397035	25-01-1994
			AU A1	22326/88	23-03-1989
			AU B2	611944	27-06-1991
			BE AF	1001685	06-02-1990
			CA A1	1326438	25-01-1994
			CH A	675968	30-11-1990
			DE A1	3822459	30-03-1989
			DE C2	3822459	07-07-1994
			DK A0	5189/88	16-09-1988
			DK A	5189/88	22-03-1989
			ES AF	2009346	16-09-1989
			FI A0	884297	19-09-1988
			FI A	884297	22-03-1989
			FI B	96919	14-06-1996
			FI C	96919	25-09-1996
			FR A1	2620621	24-03-1989
			FR B1	2620621	19-02-1993
			GB A0	8722134	28-10-1987
			GB A1	2209937	01-06-1989
			GB B2	2209937	03-07-1991
			GR A	88100619	22-06-1989
			GR B	1002244	22-04-1996
			IE B	60608	27-07-1994
			IL A0	87790	31-03-1989
			IL A1	87790	25-05-1992
			IT A0	8805213	20-09-1988
			IT A	1225148	02-11-1990
			JP A2	1121222	12-05-1989
			JP B4	7013023	15-02-1995
			LU A	87340	06-04-1989
			NL A	8802323	17-04-1989
			NO A0	884154	19-09-1988
			NO A	884154	22-03-1989
			NO B	178604	22-01-1996
			NO C	178604	02-05-1996
			PT A	88557	01-10-1988
			PT B	88557	30-11-1992
			SE A0	8803321	20-09-1988
			SE A	8803321	22-03-1989
			SE C2	503406	10-06-1996
			US A	5776885	07-07-1998
			ZA A	8806827	30-05-1989

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR 99/00071

US A	4675189	23-06-1987	AT E	21624	15-09-1986
			AU A1	77560/81	27-03-1986
			AU B2	556754	20-11-1986
			CA A1	1176365	23-10-1986
			DE C0	3175230	02-10-1986
			DE A2	523510	26-05-1986
			DE A3	523510	08-09-1986
			DE TD	523510	20-03-1986
			DE B1	523510	27-08-1986
			DE B2	523510	19-10-1986
			HK A	204789	17-03-1989
			IE B	522003	13-05-1987
			IL A0	64298	28-02-1987
			IL A1	64298	31-07-1987
			JP A2	57118512	23-07-1987
			JP B4	4040329	02-07-1987
			MY A	835/87	31-12-1987
			NZ A	198982	31-05-1985
			PH A	19942	14-08-1985
			SG A	944/87	06-05-1988
			ZA A	8107973	27-07-1983
GB A	2165517		AT A	3011/85	15-10-1990
			AT B	392586	25-04-1991
			BE A1	903463	17-02-1986
			CA A1	1259567	19-09-1989
			CH A	660303	15-04-1987
			DE A1	3536902	17-04-1986
			DE C2	3536902	01-08-1991
			DK A0	4745/85	16-10-1985
			DK A	4745/85	18-04-1986
			DK B	165355	16-11-1993
			DK C	165355	05-04-1994
			ES A1	547915	16-12-1986
			ES A5	547915	24-12-1986
			FR A1	8701493	01-03-1987
			FR A1	2571617	18-04-1986
			FR B1	2571617	19-08-1988
			GB A0	8525398	20-11-1985
			GB A1	2165517	16-04-1986
			GB B2	2165517	10-08-1986
			IE B	58245	11-08-1986
			IT A0	8505236	15-10-1985
			IT A	1187226	16-12-1987
			JP A2	61097216	15-05-1986
			NL A	8502787	16-05-1986
			NL B	192249	02-12-1986
			NL C	192249	03-04-1997
			SE A0	8504835	16-10-1985
			SE A	8504835	18-04-1986
			SE B	462780	03-09-1990
			SE C	462780	10-01-1991
			SE A	4673595	16-06-1987